

Chocking & Anchor Bolt Setting Compound

Technical Bulletin # 656G

Product Description

CHOCKFAST Gray (PR-610FR) is a specially formulated 100% solids, two component, inert filled compound developed for use in chocking non-precisely aligned equipment or in setting anchor bolts in concrete. The compound is designed to withstand severe marine and industrial environments involving a high degree of both physical and thermal shock. The compound is non-shrinking, non-burning and has a very high impact and compressive strength. Years of successful experience have shown the use of CHOCKFAST Gray to be a far superior yet less expensive method of establishing and retaining equipment alignment under extreme conditions. When poured as a continuous chock under deck equipment, CHOCKFAST Gray provides a corrosion proof moisture seal. CHOCKFAST Gray is approved or accepted for marine use by A.B.S., Lloyd's Register and other regulatory agencies.

Use & Benefits

CHOCKFAST GRAY was developed as a chocking compound for use under marine deck machinery, pumps, generators and steering gears. Industrially, the compound is used under diesel engines, generators, compressors, pumps, turbines, bearing blocks, crane rails and numerous other applications. It is also used extensively in the setting of anchor bolts into concrete.

When used as a chocking compound for machinery, the CHOCKFAST Gray provides perfectly even support without the tedious hand packing associated with conventional cement grouts. Because the compound flows readily, much thinner cross sections can be used. The compound is also completely chemical and oil resistant, will not powder or crack with age, weathering, or freeze-thaw cycling, and will seal the mounting surfaces protecting them from deterioration. Steel soleplates and rails between the machinery and the concrete foundations are not necessary with CHOCKFAST Gray.

Other successful applications of CHOCKFAST GRAY include mounting of crane rails, chocking of crane bull gears, chocking of machine shop machinery, sealing of cable penetrations, and as a filler to dampen machinery vibrations.

Design Considerations

CHOCKFAST Gray may be used where equipment alignment does NOT have to be maintained precisely AND the equipment's normal operating temperature is below 125°F (52°C). Examples of this class of machinery include winches, pumps, skid mounted diesel generators and other self-contained equipment. CHOCKFAST Gray works best when poured at a depth of between ½" to 2" (12 mm to 50 mm). Please consult your CHOCKFAST distributor or ITW Polymer Technologies if you need to pour CHOCKFAST Gray outside of these limits.

Application Instructions

CHOCKFAST Gray requires no special tools or special skills as does chocking with steel. When cast, CHOCKFAST GRAY flows readily into chock area filling all voids and conforming to all irregularities. This eliminates the machining of base plates or foundations for a perfectly fitted chock.

To facilitate mixing and pouring, store CHOCKFAST Gray at 68° to 77°F (20° to 25°C) for 12 to 24 hours prior to mixing. Pour the entire contents of the hardener container into the resin container and power mix using a Jiffy Mixing blade at 250 to 450 RPM for 3 to 5 minutes traversing the side and bottom to ensure complete mixing. Scrape the side and bottom of the container with the mixing blade. Do not allow air to be drawn into the mixture.

Precondition the surrounding metal and/or concrete surfaces to at least 55°F (13°C). Pour the mixed CHOCKFAST Gray into the overpour area of one end of a prepared mold. Allow the epoxy to flow under the mounting foot, pushing the air out ahead of it. Fill the overpour to at least 1/2" (12mm) above the mounting foot at the highest point in the chock. Do not scrape epoxy from the sides or bottom of the container when pouring.

ITW POLYMER TECHNOLOGIES

130 Commerce Drive • Montgomeryville, PA 18936 • 215-855-8450 • Fax 215-855-4688
www.chockfastgrout.com



Physical Properties

COMPRESSIVE STRENGTH	16,000 psi (1,125 kg/cm ²)	ASTM C-695
COMPRESSIVE MODULUS OF ELASTICITY	520,000 psi (36,568 kg/cm ²)	ASTM C-695
LINEAR SHRINKAGE	0.0003 in/in (0.0003 mm/mm)	ASTM D-2566
COEFFICIENT OF LINEAR THERMAL EXPANSION	16.8 x 10 ⁻⁶ /F° @ 32°F to 140°F (30.3 x 10 ⁻⁶ /C° @ 0°C to 60°C)	ASTM D-696
FLEXURAL STRENGTH		ASTM C-582
FLEXURAL MODULUS OF ELASTICITY		ASTM C-582
TENSILE STRENGTH	4,000 psi (281 kg/cm ²)	ASTM D-638
IZOD IMPACT STRENGTH	7.2 in.lbs./in. (0.32 N-m/cm)	ASTM D-256
FIRE RESISTANCE	Self-extinguishing	ASTM D-635
SERVICE TEMPERATURE	Up to 52°C (125°F)	
VIBRATION RESISTANCE	Pass 33 cps @ 0.02 in. (0.51mm) amplitude Total cycles 237,600	
THERMAL SHOCK RESISTANCE	Pass 20°F to 200°F (- 6.5°C to + 93°C)	
CORROSION RESISTANCE	Pass FTM 151A @ 96 hrs. 0.5% NaCl 96°F (35°C) Fog	
SPECIFIC GRAVITY	1.82	
HARDNESS	35-40	ASTM D-2583

Product Information

UNIT COVERAGE:	Small Unit - 187 cu.in. (3.06 liters) Large Unit - 816 cu.in. (13.37 liters)
APPLICATION TEMPERATURE	55°F (13°C) to 95°F (35°C)
UNIT WEIGHT:	<u>Small Unit:</u> Resin (NH) – 12.5 lbs. (5.6 kg), 0.76 gal (2.9 L) in a 1 gal can, Hardener (H) – 0.6 lbs., (0.3 kg), 0.3 L (9 oz) in an 8 oz plastic bottle <u>Large Unit:</u> Resin (NH) – 53.5 lbs. (24.3 kg), 3.2 gal (12 L) in a 5 gal bucket, Hardener (H) – 2.6 lbs. (1.2 kg), 40 oz (1.2 L) in a ½ gal can
UNIT SHIPPING WEIGHT	Small Unit: 5.9 kg (13 lbs), Large Unit: 56 lbs. (25.5 kg)
CURE TIME (approximate):	18 hrs. @ 85°F (30°C) 24 hrs. @ 65°F (18°C)
POT LIFE:	30-40 mins. @ 70°F (21°C)
SHELF LIFE:	18 MONTHS
CLEAN UP:	IMPAX IXT-59 Solvent or equal

Reference

Date

For design considerations and application details please request Bulletin No. 692 or contact ITW Polymer Technologies' Engineering Services Department.

06/2006

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support.

Warranty: ITW Polymer Technologies, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment.

Warranty Claims: If any product fails to meet the above, ITW Polymer Technologies will, at its option, either replace the product or refund the purchase price. ITW Polymer Technologies will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered.

Disclaimer: ITW Polymer Technologies makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose.

Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Polymer Technologies' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Polymer Technologies' election. Under no circumstances shall ITW Polymer Technologies be liable for any indirect, incidental or consequential damages.

Modification of Warranty: No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Polymer Technologies. No term of any purchase order shall serve to modify any provision of this document.

Mediation and Arbitration: If any dispute arises relating to products or product warranties, either the purchaser or ITW Polymer Technologies may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.